

(19)



Europäisches Patentamt  
European Patent Office  
Office européen des brevets



(11)

**EP 0 718 709 B1**

(12)

**EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention  
of the grant of the patent:  
**28.01.1998 Bulletin 1998/05**

(51) Int Cl.<sup>6</sup>: **G03G 9/097**

(21) Application number: **95420333.7**

(22) Date of filing: **29.11.1995**

(54) **Toners and developers containing bis(ammonium) tetrahalomanganate salts as charge-control agents**

Toner und Entwickler, die als Ladungssteuermittel Bis-(Ammonium)tetrahalomanganat-Salze enthalten

Révélateurs et agents de développement contenant des sels bisammonium de tétrahalomanganate

(84) Designated Contracting States:  
**DE FR GB**

(30) Priority: **07.12.1994 US 350592**

(43) Date of publication of application:  
**26.06.1996 Bulletin 1996/26**

(73) Proprietor: **EASTMAN KODAK COMPANY**  
**Rochester, New York 14650-2201 (US)**

(72) Inventors:  
• **Wilson, John C.**  
**Rochester, New York 14650-2201 (US)**  
• **Tyagi, Dinesh**  
**Rochester, New York 14650-2201 (US)**

(74) Representative:  
**Fevrier, Murielle Françoise E. et al**  
**KODAK INDUSTRIE**  
**Département Brevets - CRT**  
**Zone Industrielle - B.P. 21**  
**71102 Chalon-sur-Saone Cédex (FR)**

(56) References cited:  
**EP-A- 0 475 263**

- **PATENT ABSTRACTS OF JAPAN vol. 17 no. 207**  
**(P-1525), 22 April 1993 & JP-A-04 347864**  
**(MITSUBISHI) 3 December 1992,**

**EP 0 718 709 B1**

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

## Description

This invention relates to certain new electrostatographic toners and developers containing certain bis(ammonium) tetrahalomanganate salts as charge-control agents. More particularly, the salts are thermally stable and can be well-dispersed in typical toner binder materials to form the inventive toners having good charging properties.

In electrostatography, an image comprising an electrostatic field pattern, usually of non-uniform strength, (also referred to as an electrostatic latent image) is formed on an insulative surface of an electrostatographic element by any of various methods. For example, the electrostatic latent image may be formed electrophotographically (that is, by imagewise photo-induced dissipation of the strength of portions of an electrostatic field of uniform strength previously formed on a surface of an electrophotographic element comprising a photoconductive layer and an electrically conductive substrate), or it may be formed by dielectric recording (that is, by direct electrical formation of an electrostatic field pattern on a surface of a dielectric material). Typically, the electrostatic latent image is then developed into a toner image by contacting the latent image with an electrostatographic developer. If desired, the latent image can be transferred to another surface before development.

One well-known type of electrostatographic developer comprises a dry mixture of toner particles and carrier particles. Developers of this type are commonly employed in well-known electrostatographic development processes such as cascade development and magnetic brush development. The particles in such developers are formulated such that the toner particles and carrier particles occupy different positions in the triboelectric continuum, so that when they contact each other during mixing to form the developer, they become triboelectrically charged, with the toner particles acquiring a charge of one polarity and the carrier particles acquiring a charge of the opposite polarity. These opposite charges attract each other such that the toner particles cling to the surfaces of the carrier particles. When the developer is brought into contact with the latent electrostatic image, the electrostatic forces of the latent image (sometimes in combination with an additional applied field) attract the toner particles, and the toner particles are pulled away from the carrier particles and become electrostatically attached imagewise to the latent image-bearing surface. The resultant toner image can then be fixed in place on the surface by application of heat or other known methods (depending upon the nature of the surface and of the toner image) or can be transferred to another surface, to which it then can be similarly fixed.

A number of requirements are implicit in such development schemes. Namely, the electrostatic attraction between the toner and carrier particles must be strong enough to keep the toner particles held to the surfaces of the carrier particles while the developer is being transported to and brought into contact with the latent image, but when that contact occurs, the electrostatic attraction between the toner particles and the latent image must be even stronger, so that the toner particles are thereby pulled away from the carrier particles and deposited on the latent image-bearing surface. In order to meet these requirements for proper development, the level of electrostatic charge on the toner particles should be maintained within an adequate range.

The toner particles in dry developers often contain material referred to as a charge agent or a charge-control agent, which helps to establish and maintain toner charge within an acceptable range. Many types of charge-control agents have been used and are described in the published patent literature.

One general type of known charge-control agent comprises a quaternary ammonium salt. While many such salts are known, some do not perform an adequate charge-control function in any type of developer, some perform the function well in only certain kinds of developers, and some control charge well but produce adverse side effects.


A number of quaternary ammonium salt charge-control agents are described, for example, in US-A-4,684,596; US-A-4,394,430; US-A-4,338,390; US-A-4,490,455; and US-A-4,139,483. Unfortunately, many of those known charge-control agents exhibit one or more drawbacks in some developers.

For example, some of the known quaternary ammonium salt charge-control agents lack thermal stability and, thus, totally or partially decompose during attempts to mix them with known toner binder materials in well-known processes of preparing toners by mixing addenda with molten toner binders. Such processes are often referred to as melt-blending or melt-compounding processes and are commonly carried out at temperatures ranging from 120° to 150°C. Thus, charge agents that are thermally unstable at temperatures at or below 150°C can exhibit this decomposition problem.

Another important property or characteristic for a quaternary ammonium salt to possess is, as mentioned previously, the ability to establish toner charge within an acceptable range necessary for optimum toner development so that the quality of the image that is to be developed is ideal.

It would, therefore, be desirable to provide new, dry electrographic toners and developers containing ammonium salts that could perform the charge-controlling function well, while avoiding or minimizing the drawbacks noted above. The present invention provides such toners and developers.

The present invention provides new, dry particulate electrostatographic toners and developers containing charge-control agents comprising bis(ammonium) tetrahalomanganate salts having the structure:




wherein

R, R<sup>1</sup>, R<sup>2</sup> and R<sup>3</sup> are the same or different and are independently selected from hydrogen; an unsubstituted alkyl group having from 1 to 24 carbon atoms; a substituted alkyl group having from 1 to 24 carbon atoms substituted with one or more hydroxy-, carboxy-, alkoxy-, carboalkoxy-, acyloxy-, nitro-, cyano-, keto- or halo-groups; a cycloalkyl group having from 3 to 7 carbon atoms; an unsubstituted aryl group having from 6 to 14 carbon atoms; a substituted aryl group having from 6 to 14 carbon atoms substituted with one or more hydroxy-, carboxy-, alkoxy-, carboalkoxy-, acyloxy-, amino-, nitro-, cyano-, keto- or halo-groups; an alkaryl group having from 1 to 20 carbon atoms in the alkyl group and 6 to 14 carbon atoms in the aryl group; an aralkyl group having from 1 to 4 carbon atoms in the alkyl group and 6 to 14 carbon atoms in the aryl group wherein the aryl group may be unsubstituted or substituted with one or more alkyl-, hydroxy-, carboxy-, alkoxy-, carboalkoxy-, acyloxy-, amino-, nitro-, cyano-, keto-, or halo- groups; or wherein any two or more of R, R<sup>1</sup>, R<sup>2</sup>, or R<sup>3</sup> can be interconnected to one another to form a 5 to 14 membered saturated or unsaturated ring system, and X, which can be the same or different, is independently selected from fluorine, chlorine, bromine or iodine.

The inventive toners comprise a polymeric binder and a charge-control agent chosen from the salts defined above. The inventive developers comprise carrier particles and the inventive particulate toner defined above.

The salts provide good charge-control in the inventive toners and developers. The salts have decomposition points well above 150°C and are quickly, efficiently and uniformly dispersed in the inventive toners prepared by melt-blending the salts with appropriate polymeric binders.

The bis(ammonium) tetrahalomanganate salts employed in the toners and developers of the invention are those salts represented by the formula:



wherein R, R<sup>1</sup>, R<sup>2</sup> and R<sup>3</sup> are the same or different and are independently selected from hydrogen; an unsubstituted alkyl group having from 1 to 24 carbon atoms; a substituted alkyl group having from 1 to 24 carbon atoms substituted with one or more hydroxy-, carboxy-, alkoxy-, carboalkoxy-, acyloxy-, amino-, nitro-, cyano-, keto- or halo-groups; a cycloalkyl group having from 3 to 7 carbon atoms; an unsubstituted aryl group having from 6 to 14 carbon atoms; a substituted aryl group having from 6 to 14 carbon atoms substituted with one or more hydroxy-, carboxy-, alkoxy-, carboalkoxy-, acyloxy-, amino-, nitro-, cyano-, keto- or halo-groups; an alkaryl group having from 1 to 20 carbon atoms in the alkyl group and 6 to 14 carbon atoms in the aryl group; an aralkyl group having from 1 to 4 carbon atoms in the alkyl group and 6 to 14 carbon atoms in the aryl group wherein the aryl group may be unsubstituted or substituted with one or more alkyl-, hydroxy-, carboxy-, alkoxy-, carboalkoxy-, acyloxy-, amino-, nitro-, cyano-, keto- or halo-groups; or wherein any two or more of R, R<sup>1</sup>, R<sup>2</sup>, or R<sup>3</sup> can be interconnected to one another to form a 5 to 14 membered saturated or unsaturated ring system, and X, which can be the same or different, is independently selected from fluorine, chlorine, bromine or iodine.

Illustrative examples of unsubstituted alkyl groups as indicated herein include methyl, ethyl, propyl, isopropyl, butyl, isobutyl, pentyl, hexyl, heptyl, decyl, dodecyl, pentadecyl, octadecyl, docosyl, and the like.

Illustrative examples of substituted alkyl groups as indicated herein include 2-hydroxyethyl, nitromethyl, 2-chloroethyl, 2-cyanoethyl, 2-oxo-octadecyl, 2-acetoxyethyl, 3-chloropropyl, (4-methylphenylsulfonyl)methyl, 3-carbometh-

oxypropyl, 2-(3-nitropropionyloxy)ethyl, and the like.

Illustrative examples of cycloalkyl groups as indicated herein include cyclopropyl, cyclopentyl, cyclohexyl, cycloheptyl, and the like.

Illustrative examples of unsubstituted aryl groups as indicated herein include phenyl, 2-naphthyl, 2-anthryl, and the like.

Illustrative examples of substituted aryl groups as indicated herein include 3-methoxyphenyl, 4-chlorophenyl, 6-methoxy-2-naphthyl, and the like.

Illustrative examples of alkaryl groups as indicated herein include 4-methylphenyl, 4-tert-butylphenyl, 6-methyl-2-naphthyl, 2-fluorenyl, and the like.

Illustrative examples of aralkyl groups as indicated herein are benzyl, 2-phenylethyl, 3-phenylpropyl, and the like.

Illustrative examples of two or more R, R<sup>1</sup>, R<sup>2</sup> or R<sup>3</sup> groups interconnected together to form a 5 to 14 membered saturated ring system include piperidine, pyrrolidine, hexamethyleneimine, and the like.

Illustrative examples of two or more R, R<sup>1</sup>, R<sup>2</sup> or R<sup>3</sup> groups interconnected together to form a 5 to 14 membered unsaturated ring system include pyridine, quinoline, and the like.

Specific examples of salts useful in the practice of the present invention include, but are not limited to the following:

#### Specific Salts

Bis(tetraethylammonium) tetrachloromanganate, and Bis(N,N-dimethyl-N-octadecylbenzylammonium) tetrachloromanganate.

The bis(ammonium) tetrahalomanganate salts used as charge-control agents in the practice of the present invention can conveniently be prepared from an appropriate ammonium halide salt and an appropriate manganese (II) halide such as manganese (II) chloride, manganese (II) bromide or manganese (II) iodide by reacting the ammonium halide salt with the manganese (II) halide in ethanol at a 2:1 mole ratio. When manganese fluoride is used as a reactant, however, to prepare a bis(ammonium) tetrafluoromanganate salt of the invention, the reaction is carried out in hot water instead of ethanol because manganese fluoride is insoluble in ethanol.

For example, bis(tetraethylammonium)tetrachloromanganate can be prepared by dissolving an appropriate amount of tetraethylammonium chloride in ethanol and adding a solution of an appropriate amount of manganese (II) chloride-tetrahydrate in ethanol, heating the mixture to boiling, filtering the solution while hot and cooling the solution to obtain, as a solid crystalline material, bis(tetraethylammonium) tetrachloromanganate.

To be utilized as a charge-control agent in the electrostatographic toners of the invention, the bis(ammonium) salt is mixed in any convenient manner (preferably by melt-blending) with an appropriate polymeric toner binder material and any other desired addenda, and the mix is then ground to desired size to form a free-flowing powder of toner particles containing the charge agent. Other methods include those well-known in the art such as spray drying, melt dispersion and dispersion polymerization.

Toner particles of the invention have an average diameter between 0.1  $\mu\text{m}$  and 100  $\mu\text{m}$ , a value in the range from 1.0 to 30  $\mu\text{m}$  being preferable for many currently used machines. However, larger or smaller particles may be needed for particular methods of development or development conditions.

Generally, it has been found desirable to add from 0.05 to 6 parts and preferably 0.25 to 2.0 parts by weight of the aforementioned bis(ammonium) tetrahalomanganate salts per 100 parts by weight of a polymer to obtain the improved toner compositions of the present invention. Of course, it must be recognized that the optimum amount of charge-control agent to be added will depend, in part, on the particular ammonium charge-control agent selected and the particular polymer to which it is added. However, the amounts specified hereinabove are typical of the useful range of charge-control agents utilized in conventional dry-toner materials.

The polymers useful as toner binders in the practice of the present invention can be used alone or in combination and include those polymers conventionally employed in electrostatic toners. Useful amorphous polymers generally have a glass transition temperature within the range of from 50° to 120°C. Preferably, toner particles prepared from these polymers have relatively high caking temperature, for example, higher than 60°C, so that the toner powders can be stored for relatively long periods of time at fairly high temperatures without having individual particles agglomerate and clump together. The melting point of useful crystalline polymers preferably is within the range of from 65°C to 200°C so that the toner particles can readily be fused to a conventional paper receiving sheet to form a permanent image. Especially preferred crystalline polymers are those having a melting point within the range of from 65° to 120°C. Of course, where other types of receiving elements are used, for example, metal plates such as certain printing plates, polymers having a melting point or glass transition temperature higher than the values specified above can be used.

Among the various polymers which can be employed in the toner particles of the present invention are polycarbonates, resin-modified maleic alkyd polymers, polyamides, phenol-formaldehyde polymers and various derivatives thereof, polyester condensates, modified alkyd polymers, aromatic polymers containing alternating methylene and

aromatic units such as described in US-A-3,809,554 and fusible crosslinked polymers as described in U.S. Pat. No. Re. 31,072.

Typical useful toner polymers include certain polycarbonates such as those described in US-A-3,694,359, which include polycarbonate materials containing an alkylidene diarylene moiety in a recurring unit and having from 1 to 10 carbon atoms in the alkyl moiety. Other useful polymers having the above-described physical properties include polymeric esters of acrylic and methacrylic acid such as poly(alkyl acrylate), and poly(alkyl methacrylate) wherein the alkyl moiety can contain from 1 to 10 carbon atoms. Additionally, other polyesters having the aforementioned physical properties are also useful. Among such other useful polyesters are copolyesters prepared from terephthalic acid (including substituted terephthalic acid), a bis(hydroxyalkoxy)phenylalkane having from 1 to 4 carbon atoms in the alkoxy radical and from 1 to 10 carbon atoms in the alkane moiety (which can also be a halogen-substituted alkane), and an alkylene glycol having from 1 to 4 carbon atoms in the alkylene moiety.

Other useful polymers are various styrene-containing polymers. Such polymers can comprise, for example, a polymerized blend of from 40 to 100 percent by weight of styrene, from 0 to 45 percent by weight of a lower alkyl acrylate or methacrylate having from 1 to 4 carbon atoms in the alkyl moiety such as methyl, ethyl, isopropyl, butyl, and so forth and from 5 to 50 percent by weight of another vinyl monomer other than styrene, for example, a higher alkyl acrylate or methacrylate having from 6 to 20 or more carbon atoms in the alkyl group. Typical styrene-containing polymers prepared from a copolymerized blend as described hereinabove are copolymers prepared from a monomeric blend of 40 to 60 percent by weight styrene or styrene homolog, from 20 to 50 percent by weight of a lower alkyl acrylate or methacrylate and from 5 to 30 percent by weight of a higher alkyl acrylate or methacrylate such as ethylhexyl acrylate (for example, styrene-butyl acrylate-ethylhexyl acrylate copolymer). Preferred fusible styrene copolymers are those which are covalently crosslinked with a small amount of a divinyl compound such as divinylbenzene. A variety of other useful styrene-containing toner materials are disclosed in US-A-2,917,460; Re. 25,316; US-A-2,788,288; US-A-2,638,416; US-A-2,618,552 and US-A-2,659,670.

Various kinds of well-known addenda (for example, colorants, release agents, and so forth) can also be incorporated into the toners of the invention.

Numerous colorant materials selected from dyestuffs or pigments can be employed in the toner materials of the present invention. Such materials serve to color the toner and/or render it more visible. Of course, suitable toner materials having the appropriate charging characteristics can be prepared without the use of a colorant material where it is desired to have a developed image of low optical density. In those instances where it is desired to utilize a colorant, the colorants can, in principle, be selected from virtually any of the compounds mentioned in the Colour Index Volumes 1 and 2, Second Edition.

Included among the vast number of useful colorants are such materials as Hansa Yellow G (C.I. 11680), Nigrosine Spirit soluble (C.I. 50415), Chromogen Black ET00 (C.I. 45170), Solvent Black 3 (C.I. 26150), Fuchsine N (C.I. 42510), C.I. Basic Blue 9 (C.I. 52015). Carbon black also provides a useful colorant. The amount of colorant added may vary over a wide range, for example, from 1 to 20 percent of the weight of the polymer. Particularly good results are obtained when the amount is from 1 to 10 percent.

To be utilized as toners in the electrostatographic developers of the invention, the toners of this invention can be mixed with a carrier vehicle. The carrier vehicles, which can be used with the present toners to form the new developer compositions, can be selected from a variety of materials. Such materials include carrier core particles and core particles overcoated with a thin layer of a film-forming resin.

The carrier core materials can comprise conductive, non-conductive, magnetic, or non-magnetic materials. For example, carrier cores can comprise glass beads; crystals of inorganic salts such as aluminum potassium chloride; other salts such as ammonium chloride or sodium nitrate; granular zircon; granular silicon; silicon dioxide; hard resin particles such as poly(methyl methacrylate); metallic materials such as iron, steel, nickel, carborundum, cobalt, oxidized iron; or mixtures or alloys of any of the foregoing. See, for example, US-A-3,850,663 and US-A-3,970,571. Especially useful in magnetic brush development schemes are iron particles such as porous iron particles having oxidized surfaces, steel particles, and other "hard" or "soft" ferromagnetic materials such as gamma ferric oxides or ferrites, such as ferrites of barium, strontium, lead, magnesium, or aluminum. See, for example, US-A-4,042,518; US-A-4,478,925; and US-A-4,546,060.

As noted above, the carrier particles can be overcoated with a thin layer of a film-forming resin for the purpose of establishing the correct triboelectric relationship and charge level with the toner employed. Examples of suitable resins are the polymers described in US-A-3,547,822;

US-A-3,632,512; US-A-3,795,618; US-A-3,898,170 and Belgian Pat. No. 797,132. Other useful resins are fluorocarbons such as polytetrafluoroethylene, poly(vinylidene fluoride), mixtures of these and copolymers of vinylidene fluoride and tetrafluoroethylene. See, for example, US-A-4,545,060; US-A-4,478,925; US-A-4,076,857; and US-A-3,970,571. Such polymeric fluorocarbon carrier coatings can serve a number of known purposes. One such purpose can be to aid the developer to meet the electrostatic force requirements mentioned above by shifting the carrier particles to a position in the triboelectric series different from that of the uncoated carrier core material, in order to adjust the

degree of triboelectric charging of both the carrier and toner particles. Another purpose can be to reduce the frictional characteristics of the carrier particles in order to improve developer flow properties. Still another purpose can be to reduce the surface hardness of the carrier particles so that they are less likely to break apart during use and less likely to abrade surfaces (for example, photoconductive element surfaces) that they contact during use. Yet another purpose can be to reduce the tendency of toner material or other developer additives to become undesirably permanently adhered to carrier surfaces during developer use (often referred to as scumming). A further purpose can be to alter the electrical resistance of the carrier particles.

A typical developer composition containing the above-described toner and a carrier vehicle generally comprises from 1 to 20 percent by weight of particulate toner particles and from 80 to 99 percent by weight carrier particles. Usually, the carrier particles are larger than the toner particles. Conventional carrier particles have a particle size on the order of from 20 to 1200 micrometers, preferably 30-300 micrometers.

Alternatively, the toners of the present invention can be used in a single component developer, that is, with no carrier particles.

The charge-control agents of the present invention impart a positive charge to the toner composition. The level of charge on the developer compositions utilizing a charge-control agent of the present invention is preferably in the range of from 15 to 60 microcoulombs per gram of toner for toner particles having a volume average diameter of from 7 to 15 micrometers in the developer as determined in accordance with the procedure described below.

The toner and developer compositions of this invention can be used in a variety of ways to develop electrostatic charge patterns or latent images. Such developable charge patterns can be prepared by a number of means and be carried for example, on a light sensitive photoconductive element or a non-light-sensitive dielectric-surfaced element such as an insulator-coated conductive sheet. One suitable development technique involves cascading the developer composition across the electrostatic charge pattern, while another technique involves applying toner particles from a magnetic brush. This latter technique involves the use of a magnetically attractable carrier vehicle in forming the developer composition. After imagewise deposition of the toner particles, the image can be fixed, for example, by heating the toner to cause it to fuse to the substrate carrying the toner. If desired, the unfused image can be transferred to a receiver such as a blank sheet of copy paper and then fused to form a permanent image.

The following examples are presented to further illustrate the present invention.

This example describes the preparation of a charge-control agent useful in accordance with the inventions which is bis(tetraethylammonium) tetrachloromanganate.

Bis(tetraethylammonium) tetrachloromanganate was prepared by slowly adding in portions, a solution of 9.90g (0.05 mol) of  $\text{MnCl}_2 \cdot 4\text{H}_2\text{O}$  in 50 ml ethanol to a 1000 ml flask containing a solution of 16.57g (0.10 mol) of tetraethylammonium chloride in 50 ml of ethanol, adding 400 ml of ethanol, heating the mixture to boiling, filtering the mixture while hot through supercel and cooling. The product crystallized and was collected and dried to give 7.82g (34.20% of theory) of product; mp > 250 °C.

Anal. Calcd. for  $\text{C}_{16}\text{H}_{40}\text{Cl}_4\text{MnN}_2$ : C, 42.03; H, 8.82; Cl, 31.01; Mn, 12.02; N, 6.13;

Found: C, 42.10; H, 8.72; Cl, 29.3; Mn, 11.6; N, 6.14.

This example describes the preparation of a charge-control agent useful in accordance with the invention which is bis(N,N-dimethyl-N-octadecylbenzylammonium) tetrachloromanganate.

Bis(N,N-dimethyl-N-octadecylbenzylammonium) tetrachloromanganate was prepared by adding a solution of 9.90g (0.05 mol) of  $\text{MnCl}_2 \cdot 4\text{H}_2\text{O}$  in 50 ml ethanol to a 500 ml flask containing a solution of 42.42g (0.10 mol) of N,N-dimethyl-N-octadecylbenzylammonium chloride in 200 ml of ethanol, heating to dissolve and cooling in an ice-water bath. The product crystallized as a white solid which was collected, washed with a small amount of ethanol and dried to give 34.4g (70.62% of theory) of product; mp = 76-79°C.

Anal. Calcd. for  $\text{C}_{54}\text{H}_{100}\text{Cl}_4\text{MnN}_2$ : C, 66.58; H, 10.35; Cl, 14.56; Mn, 5.64; N, 2.88;

Found: C, 66.20; H, 10.25; Cl, 14.7; Mn, 5.7; N, 2.80.

The decomposition points of the bis(ammonium) tetrahalomanganate salts of Examples 1 and 2 were measured in air at 10°C/min from 25 to 500°C in a Perkin-Elmer 7 Series Thermal Analysis System. The decomposition point (temperature) of the salt of Example 1 was 316°C and the decomposition point of the salt of Example 2 was 221°C indicating that both salts are highly thermally stable for use as charge-control agents in the toners and developers of the present invention.

The salts of Examples 1 and 2 were employed and evaluated as a charge-control agent in two different concentrations in inventive toners and developers.

Inventive toner samples were formulated by compounding 100 parts of a crosslinked vinyl-addition polymer of styrene, butyl acrylate and divinylbenzene (weight ratio: 77/23/0.4), 6 parts of a carbon black pigment (Black Pearls 430 obtained from Cabot Corporation, Boston, MA); and 1 and 2 parts of the charge-control agents of Examples 1 and 2. The formulations were melt-blended on a two-roll mill at 150°C on a 4-inch (10.24 cm) roll mill, allowed to cool to room temperature and ground down to form inventive toner particles having an average particle size of approximately 12 micrometers as measured by a Coulter Counter. Inventive developers were prepared by combining 8.0 grams of

the toner particles with 92.0 grams of carrier particles comprising strontium ferrite cores which had been coated at 230°C with 2 pph of polyvinylidene fluoride (Kynar 301F manufactured by Pennwalt Corporation). Toner charges were then measured in microcoulombs per gram of toner ( $\mu\text{C/g}$ ) in a "MECCA" device according to the following procedure. The developer was vigorously shaken or "exercised" to cause triboelectric charging by placing a 4 gram sample of the developer into a glass vial, capping the vial and shaking the vial on a "wrist-action" shaker operated at about 2 Hertz and an overall amplitude of about 11 cm for 2 minutes. Toner charge level after 2 minutes of shaking was measured by placing a 0.1 to 0.2 gram sample of the charged developer in a MECCA apparatus and measuring the charge and mass of transferred toner in the MECCA apparatus. This involved placing the sample of the charged developer in a sample dish situated between electrode plates and subjecting it, simultaneously for 30 seconds, to a 60 Hz magnetic field to cause developer agitation and to an electric field of about 2000 volts/cm between the plates. The toner is released from the carrier and is attracted to and collects on the plate having a polarity opposite to the toner charge. The total toner charge is measured by an electrometer connected to the plate, and that value is divided by the weight of the toner on the plate to yield the charge per mass of toner in microcoulombs per gram ( $\mu\text{C/g}$ ). The results are shown in Table I, below.


Table I

Charge-Control Agent	Conc. (pph)	MECCA Q/M ( $\mu\text{C/g}$ )
		2 min.
Example 1	1	45.98
	2	43.03
Example 2	1	44.02
	2	51.07

The data in Table I show that the charging properties of the inventive toners and developers were good, that a high charge was attained and that the degree of charging can be controlled by varying the amount of salt which is present in the toner composition.

### Claims

1. A dry, particulate electrostatographic toner composition comprising a polymeric binder and a charge-control agent comprising a bis(ammonium) tetrahalomanganate salt having the structure:



wherein

R, R<sup>1</sup>, R<sup>2</sup> and R<sup>3</sup> are the same or different and are independently selected from hydrogen; an unsubstituted alkyl group having from 1 to 24 carbon atoms; a substituted alkyl group having from 1 to 24 carbon atoms substituted with one or more hydroxy-, carboxy-, alkoxy-, carboalkoxy-, acyloxy-, amino-, nitro-, cyano-, keto- or halo-groups; a cycloalkyl group having from 3 to 7 carbon atoms; an unsubstituted aryl group having from 6 to 14 carbon atoms; a substituted aryl group having from 6 to 14 carbon atoms substituted with one or more hydroxy-, carboxy-, alkoxy-, carboalkoxy-, acyloxy-, amino-, nitro-, cyano-, keto- or halo-groups; an alkaryl group having from 1 to 20 carbon atoms in the alkyl group and 6 to 14 carbon atoms in the aryl group; an aralkyl group having from 1 to 4 carbon atoms in the alkyl group and 6 to 14 carbon atoms in the aryl group wherein the aryl group is unsubstituted or substituted with one or more alkyl-, hydroxy-, carboxy-, alkoxy-, carboalkoxy-, acyloxy-, amino-, nitro-, cyano-, keto- or halo-groups; or wherein any two or more of R, R<sup>1</sup>, R<sup>2</sup> or R<sup>3</sup> can be interconnected to one another to form a 5 to 14 membered saturated or unsaturated ring system,


and

X, which can be the same or different, is independently selected from fluorine, chlorine, bromine or iodine.

2. The toner composition of claim 1, wherein the charge-control agent is bis(tetraethylammonium) tetrachloromanganate.
3. The toner composition of claim 1, wherein the charge-control agent is bis(N,N-dimethyl-N-octadecylbenzylammonium) tetrachloromanganate.
4. An electrostatographic developer comprising:
  - a. a particulate toner composition of claim 1, and
  - b. carrier particles.
5. The developer of claim 4, wherein the carrier particles comprise core material coated with a fluorocarbon polymer.

#### Patentansprüche

1. Trockene, teilchenförmige elektrostatische Tonerzusammensetzung mit einem polymeren Bindemittel und einem Ladungssteuermittel, umfassend ein Bis(ammonium)tetrahalomanganatsalz mit der Struktur:



worin bedeuten

R, R<sup>1</sup>, R<sup>2</sup> und R<sup>3</sup> sind gleich oder verschieden und sind unabhängig voneinander ausgewählt aus Wasserstoff; einer unsubstituierten Alkylgruppe mit 1 bis 24 Kohlenstoffatomen; einer substituierten Alkylgruppe mit 1 bis 24 Kohlenstoffatomen, substituiert durch eine oder mehrere Hydroxy-, Carboxy-, Alkoxy-, Carboalkoxy-, Acyloxy-, Amino-, Nitro-, Cyano-, Keto- oder Halogruppen; einer Cycloalkylgruppe mit 3 bis 7 Kohlenstoffatomen; einer unsubstituierten Arylgruppe mit 6 bis 14 Kohlenstoffatomen; einer substituierten Arylgruppe mit 6 bis 14 Kohlenstoffatomen, substituiert durch eine oder mehrere Hydroxy-, Carboxy-, Alkoxy-, Carboalkoxy-, Acyloxy-, Amino-, Nitro-, Cyano-, Keto- oder Halogruppen; einer Alkarylgruppe mit 1 bis 20 Kohlenstoffatomen in der Alkylgruppe und 6 bis 14 Kohlenstoffatomen in der Arylgruppe; einer Aralkylgruppe mit 1 bis 4 Kohlenstoffatomen in der Alkylgruppe und 6 bis 14 Kohlenstoffatomen in der Arylgruppe, wobei die Arylgruppe unsubstituiert ist oder substituiert durch eine oder mehrere Alkyl-, Hydroxy-, Carboxy-, Alkoxy-, Carboalkoxy-, Acyloxy-, Amino-, Nitro-, Cyano-, Keto- oder Halogruppen; oder worin beliebige zwei oder mehr von R, R<sup>1</sup>, R<sup>2</sup> oder R<sup>3</sup> miteinander verbunden sein können, unter Ausbildung eines 5- bis 14-gliedrigen gesättigten oder ungesättigten Ringsystems, und X, das gleich oder verschieden sein kann, ist unabhängig voneinander ausgewählt aus Fluor, Chlor, Brom oder Iod.


2. Tonerzusammensetzung nach Anspruch 1, in der das Ladungssteuermittel Bis(tetraethylammonium)tetrachloromanganat ist.
3. Tonerzusammensetzung nach Anspruch 1, in der das Ladungssteuermittel Bis(N,N-dimethyl-N-octadecylbenzylammonium)tetrachloromanganat ist.
4. Elektrostatischer Entwickler mit
  - a. einer teilchenförmigen Tonerzusammensetzung nach Anspruch 1, und
  - b. Trägerteilchen.



5. Entwickler nach Anspruch 4, in dem die Trägerteilchen ein Kernmaterial aufweisen, das mit einem Fluorkohlenstoffpolymeren beschichtet ist.

## 5 Revendications

1. Composition de toner électrostatographique particulaire sèche comprenant un liant polymère et un agent de contrôle de charge comprenant un sel de tétrahalomanganate de bis(ammonium) ayant la structure :



où

R, R<sup>1</sup>, R<sup>2</sup> et R<sup>3</sup> sont identiques ou différents et sont choisis séparément parmi l'hydrogène ; un groupe alkyle non substitué ayant 1 à 24 atomes de carbone ; un groupe alkyle substitué ayant 1 à 24 atomes de carbone, substitué par un ou plusieurs groupes hydroxy, carboxy, alkoxy, carboalkoxy, acyloxy, amino, nitro, cyano, céto ou halo ; un groupe cycloalkyle ayant 3 à 7 atomes de carbone ; un groupe aryle non substitué ayant 6 à 14 atomes de carbone ; un groupe aryle substitué ayant 6 à 14 atomes de carbone, substitué par un ou plusieurs groupes hydroxy, carboxy, alkoxy, carboalkoxy, acyloxy, amino, nitro, cyano, céto ou halo ; un groupe alkaryle ayant 1 à 20 atomes de carbone dans le groupe alkyle et 6 à 14 atomes de carbone dans le groupe aryle ; un groupe aralkyle ayant 1 à 4 atomes de carbone dans le groupe alkyle et 6 à 14 atomes de carbone dans le groupe aryle, dans lequel le groupe aryle est non substitué ou substitué par un ou plusieurs groupes alkyle, hydroxy, carboxy, alkoxy, carboalkoxy, acyloxy, amino, nitro, cyano, céto ou halo ; ou dans laquelle au moins deux des groupes R, R<sup>1</sup>, R<sup>2</sup> ou R<sup>3</sup> peuvent s'interconnecter pour former un système cyclique, saturé ou non, ayant 5 à 14 membres, et

X, qui peut être identique ou différent, est choisi séparément parmi le fluor, le chlore, le brome et l'iode.

2. Composition de toner selon la revendication 1, dans laquelle l'agent de contrôle de charge est un tétrachloromanganate de bis(tétraéthylammonium).
3. Composition de toner selon la revendication 1, dans laquelle l'agent de contrôle de charge est un tétrachloromanganate de bis(N,N-diméthyl-N-octadécylbenzylammonium).
4. Révélateur électrostatographique comprenant :
- une composition particulaire de toner selon la revendication 1, et
  - des particules porteuses.
5. Révélateur selon la revendication 4, dans lequel les particules porteuses comprennent un matériau central revêtu d'un polymère fluorocarboné.